



Safety Data Sheet according to Regulation (EC) No 1907/2006

Page 1 of 19

LOCTITE 2701

SDS No. : 173107
V009.0

Revision: 13.10.2016

printing date: 18.10.2016

Replaces version from: 03.08.2015

SECTION 1: Identification of the substance/mixture and of the company/undertaking

1.1. Product identifier

LOCTITE 2701

Contains:

Hydroxypropyl methacrylate
2,2'-Ethylenedioxydiethyl dimethacrylate
Methacryloyloxyethyl succinate
Cumene hydroperoxide
Acetic acid, 2-phenylhydrazide
2-Hydroxyethyl methacrylate

1.2. Relevant identified uses of the substance or mixture and uses advised against

Intended use:
Anaerobic Adhesive

1.3. Details of the supplier of the safety data sheet

Henkel Ltd
Wood Lane End
HP2 4RQ Hemel Hempstead

Great Britain

Phone: +44 1442 278000

Fax-no.: +44 1442 278071

ua-productsafety.uk@uk.henkel.com

1.4. Emergency telephone number

24 Hours Emergency Tel: +44 (0)1442 278497



SECTION 2: Hazards identification

2.1. Classification of the substance or mixture

Classification (CLP):

Serious eye irritation	Category 2
H319 Causes serious eye irritation.	
Skin sensitizer	Category 1
H317 May cause an allergic skin reaction.	
Specific target organ toxicity - single exposure	Category 3
H335 May cause respiratory irritation.	
Target organ: respiratory tract irritation	

2.2. Label elements

Label elements (CLP):

Hazard pictogram:



Signal word:

Warning

Hazard statement:

H317 May cause an allergic skin reaction.
H319 Causes serious eye irritation.
H335 May cause respiratory irritation.

Precautionary statement:

For consumer use only: P101 If medical advice is needed, have product container or label at hand. P102 Keep out of reach of children. P501 Dispose of waste and residues in accordance with local authority requirements

**Precautionary statement:
Prevention**

P261 Avoid breathing vapours.
P280 Wear protective gloves.

**Precautionary statement:
Response**

P333+P313 If skin irritation or rash occurs: Get medical advice/attention.
P337+P313 If eye irritation persists: Get medical advice/attention.

2.3. Other hazards

Non corrosive to eyes according to test method OECD 438 or based on analogy to similar products tested.
Not fulfilling Persistent, Bioaccumulative and Toxic (PBT), very Persistent and very Bioaccumulative (vPvB) criteria.

SECTION 3: Composition/information on ingredients

3.2. Mixtures

General chemical description:

Anaerobic adhesive

Declaration of the ingredients according to CLP (EC) No 1272/2008:

Hazardous components CAS-No.	EC Number REACH-Reg No.	content	Classification
Hydroxypropyl methacrylate 27813-02-1	248-666-3 01-2119490226-37	25- 50 %	Skin Sens. 1 H317 Eye Irrit. 2 H319
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	203-652-6 01-2119969287-21	5- < 10 %	Skin Sens. 1B H317
Methacryloyloxyethyl succinate 20882-04-6	244-096-4	1- < 3 %	Skin Irrit. 2; Dermal H315 Skin Sens. 1; Dermal H317 Eye Dam. 1 H318
Cumene hydroperoxide 80-15-9	201-254-7	1- < 2,5 %	Acute Tox. 4; Dermal H312 STOT RE 2 H373 Acute Tox. 4; Oral H302 Org. Perox. E H242 Acute Tox. 3; Inhalation H331 Aquatic Chronic 2 H411 Skin Corr. 1B H314
Methacrylic acid 79-41-4	201-204-4 01-2119463884-26	0,1- < 1 %	Acute Tox. 4; Oral H302 Acute Tox. 3; Dermal H311 Acute Tox. 4; Inhalation H332 Skin Corr. 1A H314
Acetic acid, 2-phenylhydrazide 114-83-0	204-055-3	0,1- < 1 %	Acute Tox. 3; Oral H301 Skin Irrit. 2 H315 Skin Sens. 1 H317 Eye Irrit. 2 H319 STOT SE 3; Inhalation H335 Carc. 2 H351
2-Hydroxyethyl methacrylate 868-77-9	212-782-2 01-2119490169-29	0,1- < 1 %	Skin Irrit. 2 H315 Skin Sens. 1 H317 Eye Irrit. 2 H319
1,4-Naphthalenedione 130-15-4	204-977-6	0,01- < 0,1 %	Acute Tox. 3; Oral H301 Skin Irrit. 2; Dermal H315 Skin Sens. 1; Dermal H317 Eye Irrit. 2 H319 Acute Tox. 1; Inhalation H330 STOT SE 3; Inhalation H335 Aquatic Acute 1 H400 Aquatic Chronic 1 H410

			M factor (Acute Aquat Tox): 10 M factor (Chron Aquat Tox): 10
--	--	--	---

**For full text of the H - statements and other abbreviations see section 16 "Other information".
Substances without classification may have community workplace exposure limits available.**

SECTION 4: First aid measures

4.1. Description of first aid measures

Inhalation:

Move to fresh air. If symptoms persist, seek medical advice.

Skin contact:

Rinse with running water and soap.

Obtain medical attention if irritation persists.

Eye contact:

Rinse immediately with plenty of running water (for 10 minutes), seek medical attention from a specialist.

Ingestion:

Rinse mouth, drink 1-2 glasses of water, do not induce vomiting, consult a doctor.

4.2. Most important symptoms and effects, both acute and delayed

EYE: Irritation, conjunctivitis.

RESPIRATORY: Irritation, coughing, shortness of breath, chest tightness.

SKIN: Rash, Urticaria.

4.3. Indication of any immediate medical attention and special treatment needed

See section: Description of first aid measures

SECTION 5: Firefighting measures

5.1. Extinguishing media

Suitable extinguishing media:

Carbon dioxide, foam, powder

Extinguishing media which must not be used for safety reasons:

None known

5.2. Special hazards arising from the substance or mixture

In the event of a fire, carbon monoxide (CO), carbon dioxide (CO₂) and nitrogen oxides (NO_x) can be released.

5.3. Advice for firefighters

Wear self-contained breathing apparatus and full protective clothing, such as turn-out gear.

Additional information:

In case of fire, keep containers cool with water spray.

SECTION 6: Accidental release measures

6.1. Personal precautions, protective equipment and emergency procedures

Avoid skin and eye contact.

6.2. Environmental precautions

Do not let product enter drains.

6.3. Methods and material for containment and cleaning up

For small spills wipe up with paper towel and place in container for disposal.

For large spills absorb onto inert absorbent material and place in sealed container for disposal.

6.4. Reference to other sections

See advice in section 8

SECTION 7: Handling and storage

7.1. Precautions for safe handling

Use only in well-ventilated areas.

Avoid skin and eye contact.

Prolonged or repeated skin contact should be avoided

Hygiene measures:

Wash hands before work breaks and after finishing work.

Do not eat, drink or smoke while working.

Good industrial hygiene practices should be observed.

7.2. Conditions for safe storage, including any incompatibilities

Store in original containers at 8-21°C (46.4-69.8°F) and do not return residual materials to containers as contamination may reduce the shelf life of the bulk product.

Refer to Technical Data Sheet

7.3. Specific end use(s)

Anaerobic Adhesive

SECTION 8: Exposure controls/personal protection

8.1. Control parameters**Occupational Exposure Limits**Valid for
Great Britain

Ingredient [Regulated substance]	ppm	mg/m ³	Value type	Short term exposure limit category / Remarks	Regulatory list
Methacrylic acid 79-41-4 [METHACRYLIC ACID]	40	143	Short Term Exposure Limit (STEL):		EH40 WEL
Methacrylic acid 79-41-4 [METHACRYLIC ACID]	20	72	Time Weighted Average (TWA):		EH40 WEL
Cumene 98-82-8 [CUMENE]	50	250	Short Term Exposure Limit (STEL):		EH40 WEL
Cumene 98-82-8 [CUMENE]			Skin designation:	Can be absorbed through the skin.	EH40 WEL
Cumene 98-82-8 [CUMENE]	25	125	Time Weighted Average (TWA):		EH40 WEL
Cumene 98-82-8 [CUMENE]	50	250	Short Term Exposure Limit (STEL):	Indicative	ECLTV
Cumene 98-82-8 [CUMENE]	20	100	Time Weighted Average (TWA):	Indicative	ECLTV

Occupational Exposure LimitsValid for
Ireland

Ingredient [Regulated substance]	ppm	mg/m ³	Value type	Short term exposure limit category / Remarks	Regulatory list
Methacrylic acid 79-41-4 [METHACRYLIC ACID]	20	70	Time Weighted Average (TWA):		IR_OEL
Methacrylic acid 79-41-4 [METHACRYLIC ACID]	40	140	Short Term Exposure Limit (STEL):		IR_OEL
Cumene 98-82-8 [ISOPROPYL BENZENE]	20	100	Time Weighted Average (TWA):	Indicative OELV	IR_OEL
Cumene 98-82-8 [ISOPROPYL BENZENE]	50	250	Short Term Exposure Limit (STEL):	Indicative OELV	IR_OEL
Cumene 98-82-8 [ISOPROPYL BENZENE]			Skin designation:	Can be absorbed through the skin.	IR_OEL
Cumene 98-82-8 [CUMENE]	50	250	Short Term Exposure Limit (STEL):	Indicative	ECLTV
Cumene 98-82-8 [CUMENE]	20	100	Time Weighted Average (TWA):	Indicative	ECLTV

Predicted No-Effect Concentration (PNEC):

Name on list	Environmental Compartment	Exposure period	Value				Remarks
			mg/l	ppm	mg/kg	others	
Methacrylic acid, monoester with propane-1,2-diol 27813-02-1	aqua (freshwater)					0,904 mg/L	
Methacrylic acid, monoester with propane-1,2-diol 27813-02-1	aqua (marine water)					0,904 mg/L	
Methacrylic acid, monoester with propane-1,2-diol 27813-02-1	sewage treatment plant (STP)					10 mg/L	
Methacrylic acid, monoester with propane-1,2-diol 27813-02-1	aqua (intermittent releases)					0,972 mg/L	
Methacrylic acid, monoester with propane-1,2-diol 27813-02-1	sediment (freshwater)				6,28 mg/kg		
Methacrylic acid, monoester with propane-1,2-diol 27813-02-1	sediment (marine water)				6,28 mg/kg		
Methacrylic acid, monoester with propane-1,2-diol 27813-02-1	soil				0,727 mg/kg		
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	aqua (freshwater)					0,164 mg/L	
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	aqua (marine water)					0,0164 mg/L	
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	sewage treatment plant (STP)					10 mg/L	
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	aqua (intermittent releases)					0,164 mg/L	
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	sediment (freshwater)				1,85 mg/kg		
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	sediment (marine water)				0,185 mg/kg		
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	soil				0,274 mg/kg		
.alpha.,.alpha.-Dimethylbenzyl hydroperoxide 80-15-9	aqua (freshwater)					0,0031 mg/L	
.alpha.,.alpha.-Dimethylbenzyl hydroperoxide 80-15-9	aqua (marine water)					0,00031 mg/L	
.alpha.,.alpha.-Dimethylbenzyl hydroperoxide 80-15-9	aqua (intermittent releases)					0,031 mg/L	
.alpha.,.alpha.-Dimethylbenzyl hydroperoxide 80-15-9	Sewage treatment plant					0,35 mg/L	
.alpha.,.alpha.-Dimethylbenzyl hydroperoxide 80-15-9	sediment (freshwater)				0,023 mg/kg		
.alpha.,.alpha.-Dimethylbenzyl hydroperoxide 80-15-9	sediment (marine water)				0,0023 mg/kg		
.alpha.,.alpha.-Dimethylbenzyl hydroperoxide 80-15-9	soil				0,0029 mg/kg		

Derived No-Effect Level (DNEL):

Name on list	Application Area	Route of Exposure	Health Effect	Exposure Time	Value	Remarks
Methacrylic acid, monoester with propane-1,2-diol 27813-02-1	Workers	dermal	Long term exposure - systemic effects		4,2 mg/kg bw/day	
Methacrylic acid, monoester with propane-1,2-diol 27813-02-1	Workers	Inhalation	Long term exposure - systemic effects		14,7 mg/m ³	
Methacrylic acid, monoester with propane-1,2-diol 27813-02-1	General population	dermal	Long term exposure - systemic effects		2,5 mg/kg bw/day	
Methacrylic acid, monoester with propane-1,2-diol 27813-02-1	General population	Inhalation	Long term exposure - systemic effects		8,8 mg/m ³	
Methacrylic acid, monoester with propane-1,2-diol 27813-02-1	General population	oral	Long term exposure - systemic effects		2,5 mg/kg bw/day	
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	Workers	inhalation	Long term exposure - systemic effects		48,5 mg/m ³	
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	Workers	dermal	Long term exposure - systemic effects		13,9 mg/kg bw/day	
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	General population	inhalation	Long term exposure - systemic effects		14,5 mg/m ³	
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	General population	dermal	Long term exposure - systemic effects		8,33 mg/kg bw/day	
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	General population	oral	Long term exposure - systemic effects		8,33 mg/kg bw/day	
.alpha.,.alpha.-Dimethylbenzyl hydroperoxide 80-15-9	Workers	inhalation	Long term exposure - systemic effects		6 mg/m ³	

Biological Exposure Indices:

None

8.2. Exposure controls:

Engineering controls:

Ensure good ventilation/extraction.

Respiratory protection:

Ensure adequate ventilation.

An approved mask or respirator fitted with an organic vapour cartridge should be worn if the product is used in a poorly ventilated area

Filter type: A (EN 14387)

Hand protection:

Chemical-resistant protective gloves (EN 374).

Suitable materials for short-term contact or splashes (recommended: at least protection index 2, corresponding to > 30 minutes permeation time as per EN 374):

nitrile rubber (NBR; \geq 0.4 mm thickness)

Suitable materials for longer, direct contact (recommended: protection index 6, corresponding to > 480 minutes permeation time as per EN 374):

nitrile rubber (NBR; \geq 0.4 mm thickness)

This information is based on literature references and on information provided by glove manufacturers, or is derived by analogy with similar substances. Please note that in practice the working life of chemical-resistant protective gloves may be considerably shorter than the permeation time determined in accordance with EN 374 as a result of the many influencing factors (e.g. temperature). If signs of wear and tear are noticed then the gloves should be replaced.

Eye protection:

Safety glasses with sideshields or chemical safety goggles should be worn if there is a risk of splashing.
Protective eye equipment should conform to EN166.

Skin protection:

Wear suitable protective clothing.

Protective clothing should conform to EN 14605 for liquid splashes or to EN 13982 for dusts.

Advices to personal protection equipment:

The information provided on personal protective equipment is for guidance purposes only. A full risk assessment should be conducted prior to using this product to determine the appropriate personal protective equipment to suit local conditions.
Personal protective equipment should conform to the relevant EN standard.

SECTION 9: Physical and chemical properties**9.1. Information on basic physical and chemical properties**

Appearance	liquid green
Odor	mild
Odour threshold	No data available / Not applicable
pH	No data available / Not applicable
Initial boiling point	> 149,0 °C (> 300.2 °F)
Flash point	> 93,00 °C (> 199.4 °F)
Decomposition temperature	No data available / Not applicable
Vapour pressure (20,0 °C (68 °F))	0,3000000 mbar
Density ()	1,1 g/cm ³
Bulk density	No data available / Not applicable
Viscosity	No data available / Not applicable
Viscosity (kinematic)	No data available / Not applicable
Explosive properties	No data available / Not applicable
Solubility (qualitative) (Solvent: Water)	Partially soluble
Solubility (qualitative) (Solvent: Acetone)	Miscible
Solidification temperature	No data available / Not applicable
Melting point	No data available / Not applicable
Flammability	No data available / Not applicable
Auto-ignition temperature	No data available / Not applicable
Explosive limits	No data available / Not applicable
Partition coefficient: n-octanol/water	No data available / Not applicable
Evaporation rate	No data available / Not applicable
Vapor density	No data available / Not applicable
Oxidising properties	No data available / Not applicable

9.2. Other information

No data available / Not applicable

SECTION 10: Stability and reactivity**10.1. Reactivity**

Reacts with strong oxidants.

10.2. Chemical stability

Stable under recommended storage conditions.

10.3. Possibility of hazardous reactions

See section reactivity

10.4. Conditions to avoid

No decomposition if used according to specifications.

10.5. Incompatible materials

See section reactivity.

10.6. Hazardous decomposition products

carbon oxides.

SECTION 11: Toxicological information**11.1. Information on toxicological effects****General toxicological information:**

The mixture is classified based on the available hazard information for the ingredients as defined in the classification criteria for mixtures for each hazard class or differentiation in Annex I to Regulation (EC) No 1272/2008. Relevant available health/ecological information for the substances listed under Section 3 is provided in the following.

STOT-single exposure:

May cause respiratory irritation.

Oral toxicity:

May cause irritation to the digestive tract.

Skin irritation:

Prolonged or repeated contact may cause skin irritation.

Eye irritation:

Causes serious eye irritation.

Non corrosive to eyes according to test method OECD 438 or based on analogy to similar products tested.

Sensitizing:

May cause an allergic skin reaction.

Acute oral toxicity:

Hazardous components CAS-No.	Value type	Value	Route of application	Exposure time	Species	Method
Hydroxypropyl methacrylate 27813-02-1	LD50	> 2.000 mg/kg	oral		rat	OECD Guideline 401 (Acute Oral Toxicity)
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	LD50	10.837 mg/kg	oral		rat	not specified
Methacryloyloxyethyl succinate 20882-04-6	LD50	> 2.000 mg/kg	oral		rat	OECD Guideline 423 (Acute Oral toxicity)
Cumene hydroperoxide 80-15-9	LD50	550 mg/kg	oral		rat	not specified
Methacrylic acid 79-41-4	LD50	1.320 mg/kg	oral		rat	OECD Guideline 401 (Acute Oral Toxicity)
1,4-Naphthalenedione 130-15-4	LD50	190 mg/kg	oral		rat	not specified

Acute inhalative toxicity:

Hazardous components CAS-No.	Value type	Value	Route of application	Exposure time	Species	Method
Methacrylic acid 79-41-4	LC50	> 3,6 mg/l	aerosol	4 h	rat	OECD Guideline 403 (Acute Inhalation Toxicity)

Acute dermal toxicity:

Hazardous components CAS-No.	Value type	Value	Route of application	Exposure time	Species	Method
Hydroxypropyl methacrylate 27813-02-1	LD50	> 5.000 mg/kg	dermal		rabbit	not specified
Cumene hydroperoxide 80-15-9	LD50	1.200 - 1.520 mg/kg	dermal			not specified
Methacrylic acid 79-41-4	Acute toxicity estimate (ATE)	500 mg/kg	dermal			Expert judgement
Methacrylic acid 79-41-4	LD50	500 - 1.000 mg/kg			rabbit	Dermal Toxicity Screening
2-Hydroxyethyl methacrylate 868-77-9	LD50	> 3.000 mg/kg	dermal		rabbit	not specified

Skin corrosion/irritation:

Hazardous components CAS-No.	Result	Exposure time	Species	Method
Hydroxypropyl methacrylate 27813-02-1	not irritating	24 h	rabbit	Draize Test
Methacryloyloxyethyl succinate 20882-04-6	not irritating	0,25 h	Human, EPISKIIN™ Reconstitute d Human Epidermis model	OECD Guideline 439 (In Vitro Skin Irritation: Reconstructed Human Epidermis (RHE) Test Method)
Methacryloyloxyethyl succinate 20882-04-6	Not Classified	4 h	Human, EPISKIIN™ Reconstitute d Human Epidermis model	OECD Guideline 431 (In Vitro Skin Corrosion: Reconstructed Human Epidermis (RHE) Test Method)
Cumene hydroperoxide 80-15-9	corrosive		rabbit	Draize Test
Methacrylic acid 79-41-4	Category 1A (corrosive)	4 h	rabbit	OECD Guideline 404 (Acute Dermal Irritation / Corrosion)

Serious eye damage/irritation:

Hazardous components CAS-No.	Result	Exposure time	Species	Method
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	slightly irritating	24 h	rabbit	OECD Guideline 405 (Acute Eye Irritation / Corrosion)
Methacrylic acid 79-41-4	Category I		rabbit	Draize Test

Respiratory or skin sensitization:

Hazardous components CAS-No.	Result	Test type	Species	Method
Methacrylic acid 79-41-4	not sensitising	Buehler test	guinea pig	OECD Guideline 406 (Skin Sensitisation)

Germ cell mutagenicity:

Hazardous components CAS-No.	Result	Type of study / Route of administration	Metabolic activation / Exposure time	Species	Method
Hydroxypropyl methacrylate 27813-02-1	negative	bacterial reverse mutation assay (e.g Ames test)	with and without		OECD Guideline 471 (Bacterial Reverse Mutation Assay)
	negative	mammalian cell gene mutation assay	with and without		OECD Guideline 476 (In vitro Mammalian Cell Gene Mutation Test)
Hydroxypropyl methacrylate 27813-02-1	negative	oral: gavage		rat	OECD Guideline 474 (Mammalian Erythrocyte Micronucleus Test)
Methacryloyloxyethyl succinate 20882-04-6	negative	bacterial reverse mutation assay (e.g Ames test)	with and without		OECD Guideline 471 (Bacterial Reverse Mutation Assay)
Cumene hydroperoxide 80-15-9	positive	bacterial reverse mutation assay (e.g Ames test)	without		OECD Guideline 471 (Bacterial Reverse Mutation Assay)
Cumene hydroperoxide 80-15-9	negative	dermal		mouse	not specified
Methacrylic acid 79-41-4	negative	bacterial reverse mutation assay (e.g Ames test)	with and without		OECD Guideline 471 (Bacterial Reverse Mutation Assay)
Methacrylic acid 79-41-4	negative	inhalation		mouse	OECD Guideline 478 (Genetic Toxicology: Rodent Dominant Lethal Test)
2-Hydroxyethyl methacrylate 868-77-9	negative	bacterial reverse mutation assay (e.g Ames test)	with and without		OECD Guideline 471 (Bacterial Reverse Mutation Assay)
	positive	in vitro mammalian chromosome aberration test	with and without		OECD Guideline 473 (In vitro Mammalian Chromosome Aberration Test)

Carcinogenicity:

Hazardous components CAS-No.	Result	Species	Sex	Exposure time Frequency of treatment	Route of application	Method
Hydroxypropyl methacrylate 27813-02-1		rat	male	2 years (102 weeks) 6 hours/day, 5 days/week	inhalation	OECD Guideline 451 (Carcinogenicity Studies)

Reproductive toxicity:

Hazardous substances CAS-No.	Result / Classification	Species	Exposure time	Species	Method
Hydroxypropyl methacrylate 27813-02-1	NOAEL P = 400 mg/kg	two- generation study oral: gavage	until one day before sacrifice	rat	OECD Guideline 416 (Two- Generation Reproduction Toxicity Study)

Repeated dose toxicity

Hazardous components CAS-No.	Result	Route of application	Exposure time / Frequency of treatment	Species	Method
Hydroxypropyl methacrylate 27813-02-1	NOAEL=300 mg/kg	oral: gavage		rat	OECD Guideline 422 (Combined Repeated Dose Toxicity Study with the Reproduction / Developmental Toxicity Screening Test)
Cumene hydroperoxide 80-15-9		inhalation: aerosol	6 h/d5 d/w	rat	not specified

SECTION 12: Ecological information

General ecological information:

The mixture is classified based on the available hazard information for the ingredients as defined in the classification criteria for mixtures for each hazard class or differentiation in Annex I to Regulation (EC) No 1272/2008. Relevant available health/ecological information for the substances listed under Section 3 is provided in the following.

12.1. Toxicity

Ecotoxicity:

Do not empty into drains / surface water / ground water.

Hazardous components CAS-No.	Value type	Value	Acute Toxicity Study	Exposure time	Species	Method
Hydroxypropyl methacrylate 27813-02-1	LC50	493 mg/l	Fish	48 h	Leuciscus idus melanotus	DIN 38412-15
Hydroxypropyl methacrylate 27813-02-1	EC50	> 143 mg/l	Daphnia	48 h	Daphnia magna	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Hydroxypropyl methacrylate 27813-02-1	EC50	> 97,2 mg/l	Algae	72 h	Pseudokirchnerella subcapitata	OECD Guideline 201 (Alga, Growth Inhibition Test)
	NOEC	> 97,2 mg/l	Algae	72 h	Pseudokirchnerella subcapitata	OECD Guideline 201 (Alga, Growth Inhibition Test)
Hydroxypropyl methacrylate 27813-02-1	EC10	1.140 mg/l	Bacteria	16 h		
Hydroxypropyl methacrylate 27813-02-1	NOEC	45,2 mg/l	chronic Daphnia	21 d	Daphnia magna	OECD 211 (Daphnia magna, Reproduction Test)
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	LC50	16,4 mg/l	Fish	96 h		OECD Guideline 203 (Fish, Acute Toxicity Test)
Methacryloyloxyethyl succinate 20882-04-6	EC50	> 515,4 mg/l	Daphnia	48 h	Daphnia magna	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Methacryloyloxyethyl succinate 20882-04-6	EC50	> 312 mg/l	Algae	72 h	Pseudokirchnerella subcapitata	OECD Guideline 201 (Alga, Growth Inhibition Test)
Cumene hydroperoxide 80-15-9	LC50	3,9 mg/l	Fish	96 h	Oncorhynchus mykiss	OECD Guideline 203 (Fish, Acute Toxicity Test)
Cumene hydroperoxide 80-15-9	EC50	18 mg/l	Daphnia	48 h	Daphnia magna	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Cumene hydroperoxide 80-15-9	ErC50	3,1 mg/l	Algae	72 h	Pseudokirchnerella subcapitata	OECD Guideline 201 (Alga, Growth Inhibition Test)
Cumene hydroperoxide 80-15-9	EC10	70 mg/l	Bacteria	30 min		
Methacrylic acid 79-41-4	LC50	85 mg/l	Fish	96 h	Salmo gairdneri (new name: Oncorhynchus mykiss)	EPA OTS 797.1400 (Fish Acute Toxicity Test)
Methacrylic acid 79-41-4	EC50	> 130 mg/l	Daphnia	48 h	Daphnia magna	EPA OTS 797.1300 (Aquatic Invertebrate Acute Toxicity Test, Freshwater Daphnids)
Methacrylic acid 79-41-4	NOEC	8,2 mg/l	Algae	72 h	Selenastrum capricornutum (new name: Pseudokirchnerella subcapitata)	OECD Guideline 201 (Alga, Growth Inhibition Test)
	EC50	45 mg/l	Algae	72 h	Selenastrum capricornutum (new name: Pseudokirchnerella subcapitata)	OECD Guideline 201 (Alga, Growth Inhibition Test)
Methacrylic acid 79-41-4	EC10	100 mg/l	Bacteria	17 h		
2-Hydroxyethyl methacrylate 868-77-9	LC50	227 mg/l	Fish	96 h	Pimephales promelas	OECD Guideline 203 (Fish, Acute Toxicity Test)
2-Hydroxyethyl methacrylate 868-77-9	EC50	380 mg/l	Daphnia	48 h	Daphnia magna	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
2-Hydroxyethyl methacrylate 868-77-9	EC50	345 mg/l	Algae	72 h	Selenastrum capricornutum (new name: Pseudokirchnerella subcapitata)	OECD Guideline 201 (Alga, Growth Inhibition Test)
	NOEC	160 mg/l	Algae	72 h	Selenastrum capricornutum (new name: Pseudokirchnerella subcapitata)	OECD Guideline 201 (Alga, Growth Inhibition Test)
2-Hydroxyethyl methacrylate	EC0	> 3.000 mg/l	Bacteria	16 h		

868-77-9 2-Hydroxyethyl methacrylate 868-77-9	NOEC	24,1 mg/l	chronic Daphnia	21 d	Daphnia magna	OECD 211 (Daphnia magna, Reproduction Test) OECD Guideline 201 (Alga, Growth Inhibition Test)
1,4-Naphthalenedione 130-15-4	EC50	0,011 mg/l	Algae	72 h	Dunaliella bioculata	

12.2. Persistence and degradability

Persistence and Biodegradability:

The product is not biodegradable.

Hazardous components CAS-No.	Result	Route of application	Degradability	Method
Hydroxypropyl methacrylate 27813-02-1	readily biodegradable	aerobic	94,2 %	OECD Guideline 301 E (Ready biodegradability: Modified OECD Screening Test)
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	readily biodegradable		85 %	OECD Guideline 301 B (Ready Biodegradability: CO2 Evolution Test)
Methacryloyloxyethyl succinate 20882-04-6	readily biodegradable, but failing 10-day window	aerobic	80 %	OECD Guideline 301 F (Ready Biodegradability: Manometric Respirometry Test)
Cumene hydroperoxide 80-15-9		no data	0 %	OECD Guideline 301 B (Ready Biodegradability: CO2 Evolution Test)
Methacrylic acid 79-41-4	inherently biodegradable	aerobic	100 %	OECD Guideline 302 B (Inherent biodegradability: Zahn- Wellens/EMPA Test)
	readily biodegradable	aerobic	86 %	OECD Guideline 301 D (Ready Biodegradability: Closed Bottle Test)
2-Hydroxyethyl methacrylate 868-77-9	readily biodegradable	aerobic	92 - 100 %	OECD Guideline 301 C (Ready Biodegradability: Modified MITI Test (I))
1,4-Naphthalenedione 130-15-4		no data	0 - 60 %	OECD 301 A - F

12.3. Bioaccumulative potential / 12.4. Mobility in soil

Mobility:

Cured adhesives are immobile.

Bioaccumulative potential:

No data available for the product.

Hazardous components CAS-No.	LogPow	Bioconcentration factor (BCF)	Exposure time	Species	Temperature	Method
Hydroxypropyl methacrylate 27813-02-1	0,97				20 °C	not specified
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	1,88					not specified
Methacryloyloxyethyl succinate 20882-04-6	0,783				23 °C	EU Method A.8 (Partition Coefficient)
Cumene hydroperoxide 80-15-9		9,1		calculation		OECD Guideline 305 (Bioconcentration: Flow- through Fish Test) not specified
Cumene hydroperoxide 80-15-9	2,16					
Methacrylic acid 79-41-4	0,93				22 °C	OECD Guideline 107 (Partition Coefficient (n- octanol / water), Shake Flask Method)
Acetic acid, 2- phenylhydrazide 114-83-0	0,74					not specified
1,4-Naphthalenedione 130-15-4	1,71					not specified

12.5. Results of PBT and vPvB assessment

Hazardous components CAS-No.	PBT/vPvB
Hydroxypropyl methacrylate 27813-02-1	Not fulfilling Persistent, Bioaccumulative and Toxic (PBT), very Persistent and very Bioaccumulative (vPvB) criteria.
2,2'-Ethylenedioxydiethyl dimethacrylate 109-16-0	Not fulfilling Persistent, Bioaccumulative and Toxic (PBT), very Persistent and very Bioaccumulative (vPvB) criteria.
Cumene hydroperoxide 80-15-9	Not fulfilling Persistent, Bioaccumulative and Toxic (PBT), very Persistent and very Bioaccumulative (vPvB) criteria.
Methacrylic acid 79-41-4	Not fulfilling Persistent, Bioaccumulative and Toxic (PBT), very Persistent and very Bioaccumulative (vPvB) criteria.
2-Hydroxyethyl methacrylate 868-77-9	Not fulfilling Persistent, Bioaccumulative and Toxic (PBT), very Persistent and very Bioaccumulative (vPvB) criteria.

12.6. Other adverse effects

No data available.

SECTION 13: Disposal considerations**13.1. Waste treatment methods**

Product disposal:

Dispose of in accordance with local and national regulations.

Disposal of uncleaned packages:

After use, tubes, cartons and bottles containing residual product should be disposed of as chemically contaminated waste in an authorised legal land fill site or incinerated.

Disposal must be made according to official regulations.

Waste code

08 04 09 waste adhesives and sealants containing organic solvents and other dangerous substances

The valid EWC waste code numbers are source-related. The manufacturer is therefore unable to specify EWC waste codes for the articles or products used in the various sectors. The EWC codes listed are intended as a recommendation for users. We will be happy to advise you.

SECTION 14: Transport information

- 14.1. UN number**
Not hazardous according to RID, ADR, ADN, IMDG, IATA-DGR.
- 14.2. UN proper shipping name**
Not hazardous according to RID, ADR, ADN, IMDG, IATA-DGR.
- 14.3. Transport hazard class(es)**
Not hazardous according to RID, ADR, ADN, IMDG, IATA-DGR.
- 14.4. Packing group**
Not hazardous according to RID, ADR, ADN, IMDG, IATA-DGR.
- 14.5. Environmental hazards**
Not hazardous according to RID, ADR, ADN, IMDG, IATA-DGR.
- 14.6. Special precautions for user**
Not hazardous according to RID, ADR, ADN, IMDG, IATA-DGR.
- 14.7. Transport in bulk according to Annex II of Marpol and the IBC Code**
not applicable

SECTION 15: Regulatory information

15.1. Safety, health and environmental regulations/legislation specific for the substance or mixture

VOC content < 3 %
(2010/75/EC)

15.2. Chemical safety assessment

A chemical safety assessment has not been carried out.

SECTION 16: Other information

The labelling of the product is indicated in Section 2. The full text of all abbreviations indicated by codes in this safety data sheet are as follows:

- H242 Heating may cause a fire.
- H301 Toxic if swallowed.
- H302 Harmful if swallowed.
- H311 Toxic in contact with skin.
- H312 Harmful in contact with skin.
- H314 Causes severe skin burns and eye damage.
- H315 Causes skin irritation.
- H317 May cause an allergic skin reaction.
- H318 Causes serious eye damage.
- H319 Causes serious eye irritation.
- H330 Fatal if inhaled.
- H331 Toxic if inhaled.
- H332 Harmful if inhaled.
- H335 May cause respiratory irritation.
- H351 Suspected of causing cancer.
- H373 May cause damage to organs through prolonged or repeated exposure.
- H400 Very toxic to aquatic life.
- H410 Very toxic to aquatic life with long lasting effects.
- H411 Toxic to aquatic life with long lasting effects.

Further information:

This information is based on our current level of knowledge and relates to the product in the state in which it is delivered. It is intended to describe our products from the point of view of safety requirements and is not intended to guarantee any particular properties.

Label elements (DPD):

Xi - Irritant



Risk phrases:

- R36/37 Irritating to eyes and respiratory system.
- R43 May cause sensitisation by skin contact.

Safety phrases:

- S23 Do not breathe vapour.
- S24 Avoid contact with skin.
- S26 In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- S37 Wear suitable gloves.

Additional labeling:

For consumer use only: S2 Keep out of the reach of children.
S46 If swallowed, seek medical advice immediately and show this container or label.

Contains:

- Hydroxypropyl methacrylate,
- 2,2'-Ethylenedioxydiethyl dimethacrylate,
- Methacryloyloxyethyl succinate

Relevant changes in this safety data sheet are indicated by vertical lines at the left margin in the body of this document. Corresponding text is displayed in a different color on shadowed fields.



LOCTITE® 2701

June 2004

PRODUCT DESCRIPTION

LOCTITE® 2701 provides the following product characteristics:

Technology	Acrylic
Chemical Type	Dimethacrylate ester
Appearance (uncured)	Green liquid ^{LMS}
Fluorescence	Positive under UV light ^{LMS}
Components	One component - requires no mixing
Viscosity	Low
Cure	Anaerobic
Secondary Cure	Activator
Application	Threadlocking
Strength	High

LOCTITE® 2701 is designed for the permanent locking and sealing of threaded fasteners. The product cures when confined in the absence of air between close fitting metal surfaces and prevents loosening and leakage from shock and vibration. This product is particularly suited for use on inactive substrates and/or where maximum resistance to hot oil is required.


TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.08
Flash Point - See MSDS	
Viscosity, Brookfield - RVT, 25 °C, mPa·s (cP): Spindle 2, speed 20 rpm	500 to 900 ^{LMS}

TYPICAL CURING PERFORMANCE


Cure Speed vs. Substrate

The rate of cure will depend on the substrate used. The graph below shows the shear strength developed with time on steel pins and collars compared to different materials and tested according to ISO 10123.




Cure Speed vs. Bond Gap

The rate of cure will depend on the bondline gap. The following graph shows shear strength developed with time on steel pins and collars at different controlled gaps and tested according to ISO 10123.




Cure Speed vs. Temperature

The rate of cure will depend on the temperature. The graph below shows the shear strength developed with time at different temperatures on steel pins and collars and tested according to ISO 10123.



Cure Speed vs. Activator

Where cure speed is unacceptably long, or large gaps are present, applying activator to the surface will improve cure speed. The graph below shows shear strength developed with time using Activator 7471 and 7649 on zinc dichromate steel pins and collars and tested according to ISO 10123.



TYPICAL PROPERTIES OF CURED MATERIAL**Physical Properties:**

Coefficient of Thermal Expansion, ASTM D 696, K ⁻¹	100×10 ⁻⁶
Coefficient of Thermal Conductivity, ASTM C 177, W/(m·K)	0.10
Specific Heat, kJ/(kg·K)	0.30

TYPICAL PERFORMANCE OF CURED MATERIAL**Adhesive Properties**

After 24 hours @ 22 °C

Breakaway Torque, ISO 10964:

M10 black oxide steel nuts and bolts	N·m	26 to 50
	(lb.in.)	(230 to 440)

Prevail Torque, ISO 10964:

M10 black oxide steel nuts and bolts	N·m	≥15 ^{LMS}
	(lb.in.)	(≥132)

Breakloose Torque, ISO 10964, Pre-torqued to 5 N·m:

M10 black oxide steel nuts and bolts	N·m	30 to 60
	(lb.in.)	(265 to 530)

Max. Prevail Torque, ISO 10964, Pre-torqued to 5 N·m:


M10 black oxide steel nuts and bolts	N·m	36 to 60
	(lb.in.)	(320 to 530)

Compressive Shear Strength, ISO 10123:

Steel pins and collars	N/mm ²	18 to 30
	(psi)	(2,610 to 4,350)

Torque Augmentation

Breakloose torque of an uncoated fastener will normally be 15 to 30% less than the on-torque. The effect of LOCTITE® 2701 on the breakloose torque is shown in the graph below.

**TYPICAL ENVIRONMENTAL RESISTANCE**


Cured for 1 week @ 22 °C

Breakloose Torque, ISO 10964, Pre-torqued to 5 N·m:


M10 zinc phosphate steel nuts and bolts

Hot Strength

Tested at temperature

**Heat Aging**

Aged at temperature indicated and tested @ 22 °C

**Chemical/Solvent Resistance**

Aged under conditions indicated and tested @ 22°C.

Environment	°C	% of initial strength		
		100 hr	500 hr	1000 hr
Motor Oil	125	95	100	110
Gasoline	22	100	110	115
Brake fluid	22	100	100	105
Ethanol	22	95	95	95
Acetone	22	100	100	100
1,1,1 Trichloroethane	22	100	110	110
Water Glycol 50/50	87	100	100	100

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure and performance of the adhesive.

This product is not normally recommended for use on plastics (particularly thermoplastic materials where stress cracking of the plastic could result). Users are recommended to confirm compatibility of the product with such substrates.

Directions for use**For Assembly**

1. For best results, clean all surfaces (external and internal) with a Loctite cleaning solvent and allow to dry.
2. If the material is an inactive metal or the cure speed is to slow, spray all threads with Activator 7471 or 7649 and allow to dry.
3. To prevent the product from clogging in the nozzle, do not allow the tip to touch metal surfaces during application.
4. **For Thru Holes**, apply several drops of the product onto the bolt at the nut engagement area.
5. **For Blind Holes**, apply several drops of the product down the internal threads to the bottom of the hole.
6. **For Sealing Applications**, apply a 360° bead of product to the leading threads of the male fitting, leaving the first thread free. Force the material into the threads to thoroughly fill the voids. For bigger threads and voids, adjust product amount accordingly and apply a 360° bead of product on the female threads also.
7. Assemble and tighten as required.

For Disassembly

1. Apply localized heat to nut or bolt to approximately 250 °C. Disassemble while hot.

For Cleanup

1. Cured product can be removed with a combination of soaking in a Loctite solvent and mechanical abrasion such as a wire brush.

Loctite Material Specification^{LMS}

LMS dated February 27, 1998. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Loctite Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 N x 0.225 = lb
 N/mm x 5.71 = lb/in
 N/mm² x 145 = psi
 MPa x 145 = psi
 N·m x 8.851 = lb·in
 N·mm x 0.142 = oz·in
 mPa·s = cP

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

LOCTITE is a trademark of Henkel Corporation

Reference 1