



## Safety Data Sheet according to (EC) No 1907/2006

Page 1 of 14

Loctite 480

SDS No. : 153522  
V003.2

Revision: 14.07.2015

printing date: 16.12.2016

Replaces version from: 29.04.2015

### SECTION 1: Identification of the substance/mixture and of the company/undertaking

#### 1.1. Product identifier

Loctite 480

#### Contains:

Ethyl 2-cyanoacrylate

#### 1.2. Relevant identified uses of the substance or mixture and uses advised against

Intended use:

Adhesive

#### 1.3. Details of the supplier of the safety data sheet

Henkel Ltd

Wood Lane End

HP2 4RQ Hemel Hempstead

Great Britain

Phone: +44 1442 278000

Fax-no.: +44 1442 278071

ua-productsafety.uk@uk.henkel.com

#### 1.4. Emergency telephone number

24 Hours Emergency Tel: +44 (0)1442 278497

### SECTION 2: Hazards identification

#### 2.1. Classification of the substance or mixture

##### Classification (CLP):

Skin irritation	Category 2
H315 Causes skin irritation.	
Serious eye irritation	Category 2
H319 Causes serious eye irritation.	
Specific target organ toxicity - single exposure	Category 3
H335 May cause respiratory irritation.	
Target organ: respiratory tract irritation	
Chronic hazards to the aquatic environment	Category 3
H412 Harmful to aquatic life with long lasting effects.	

#### 2.2. Label elements

##### Label elements (CLP):

**Hazard pictogram:**



**Signal word:**

Warning

**Hazard statement:**

H315 Causes skin irritation.  
H319 Causes serious eye irritation.  
H335 May cause respiratory irritation.  
H412 Harmful to aquatic life with long lasting effects.

**Supplemental information**

EUH202 Cyanoacrylate. Danger. Bonds skin and eyes in seconds. Keep out of the reach of children.  
Contains Phthalic anhydride; Hydroquinone. May produce an allergic reaction.

**Precautionary statement:  
Prevention**

P261 Avoid breathing vapours.  
P273 Avoid release to the environment.  
P280 Wear protective gloves/eye protection.

**Precautionary statement:  
Response**

P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.  
P337+P313 If eye irritation persists: Get medical advice/attention.

**Precautionary statement:  
Disposal**

P501 Dispose of waste and residues in accordance with local authority requirements.

**2.3. Other hazards**  
None if used properly.

**SECTION 3: Composition/information on ingredients**

**3.2. Mixtures**

**General chemical description:**  
Cyanoacrylate Adhesive

**Declaration of the ingredients according to CLP (EC) No 1272/2008:**

<b>Hazardous components CAS-No.</b>	<b>EC Number REACH-Reg No.</b>	<b>content</b>	<b>Classification</b>
Ethyl 2-cyanoacrylate 7085-85-0	230-391-5 01-2119527766-29	50- 100 %	Eye Irrit. 2 H319 STOT SE 3 H335 Skin Irrit. 2 H315
Hydroquinone 123-31-9	204-617-8 01-2119524016-51	0,25- < 1 %	Aquatic Acute 1 H400 Aquatic Chronic 1 H410 Carc. 2 H351 Muta. 2 H341 Acute Tox. 4; Oral H302 Eye Dam. 1 H318 Skin Sens. 1 H317 M factor: 10
Phthalic anhydride 85-44-9	201-607-5 01-2119457017-41	0,1- < 1 %	Acute Tox. 4; Oral H302 STOT SE 3 H335 Skin Irrit. 2 H315 Eye Dam. 1 H318 Resp. Sens. 1 H334 Skin Sens. 1 H317

**For full text of the H - statements and other abbreviations see section 16 "Other information".  
Substances without classification may have community workplace exposure limits available.**

**SECTION 4: First aid measures****4.1. Description of first aid measures****Inhalation:**

Move to fresh air, consult doctor if complaint persists.

**Skin contact:**

Do not pull bonded skin apart. It may be gently peeled apart using a blunt object such as a spoon, preferably after soaking in warm soapy water.

Cyanoacrylates give off heat on solidification. In rare cases a large drop will generate enough heat to cause a burn.

Burns should be treated normally after the adhesive has been removed from the skin.

If lips are accidentally stuck together apply warm water to the lips and encourage maximum wetting and pressure from saliva inside the mouth.

Peel or roll lips apart. Do not try to pull the lips apart with direct opposing action.

**Eye contact:**

If the eye is bonded closed, release eyelashes with warm water by covering with wet pad.

Cyanoacrylate will bond to eye protein and will cause periods of weeping which will help to debond the adhesive.

Keep eye covered until debonding is complete, usually within 1-3 days.

Do not force eye open. Medical advice should be sought in case solid particles of cyanoacrylate trapped behind the eyelid cause any abrasive damage.

**Ingestion:**

Ensure that breathing passages are not obstructed. The product will polymerise immediately in the mouth making it almost impossible to swallow. Saliva will slowly separate the solidified product from the mouth (several hours).

**4.2. Most important symptoms and effects, both acute and delayed**

**EYE:** Irritation, conjunctivitis.

**SKIN:** Redness, inflammation.

**RESPIRATORY:** Irritation, coughing, shortness of breath, chest tightness.

**4.3. Indication of any immediate medical attention and special treatment needed**

See section: Description of first aid measures

## SECTION 5: Firefighting measures

**5.1. Extinguishing media**

**Suitable extinguishing media:**

Foam, extinguishing powder, carbon dioxide.

Fine water spray

**Extinguishing media which must not be used for safety reasons:**

None known

**5.2. Special hazards arising from the substance or mixture**

In case of fire, keep containers cool with water spray.

Oxides of carbon, oxides of nitrogen, irritating organic vapors.

**5.3. Advice for firefighters**

Fire fighters should wear positive pressure self-contained breathing apparatus (SCBA).

**Additional information:**

In case of fire, keep containers cool with water spray.

## SECTION 6: Accidental release measures

**6.1. Personal precautions, protective equipment and emergency procedures**

Ensure adequate ventilation.

**6.2. Environmental precautions**

Do not let product enter drains.

**6.3. Methods and material for containment and cleaning up**

Do not use cloths for mopping up. Flood with water to complete polymerization and scrape off the floor. Cured material can be disposed of as non-hazardous waste.

**6.4. Reference to other sections**

See advice in section 8

## SECTION 7: Handling and storage

**7.1. Precautions for safe handling**

Ventilation (low level) is recommended when using large volumes

Use of dispensing equipment is recommended to minimise the risk of skin or eye contact

Avoid skin and eye contact.

See advice in section 8

**Hygiene measures:**

Wash hands before work breaks and after finishing work.

Do not eat, drink or smoke while working.

Good industrial hygiene practices should be observed.

**7.2. Conditions for safe storage, including any incompatibilities**

For optimum shelf life store in original containers under refrigerated conditions at 2 - 8°C (35.6 - 46.4 °F)

**7.3. Specific end use(s)**

Adhesive

**SECTION 8: Exposure controls/personal protection****8.1. Control parameters****Occupational Exposure Limits**Valid for  
Great Britain

Ingredient [Regulated substance]	ppm	mg/m <sup>3</sup>	Value type	Short term exposure limit category / Remarks	Regulatory list
Ethyl 2-cyanoacrylate 7085-85-0 [ETHYL CYANOACRYLATE]	0,3	1,5	Short Term Exposure Limit (STEL):		EH40 WEL
Carbon black 1333-86-4 [CARBON BLACK]		7	Short Term Exposure Limit (STEL):		EH40 WEL
Carbon black 1333-86-4 [CARBON BLACK]		3,5	Time Weighted Average (TWA):		EH40 WEL
Phthalic anhydride 85-44-9 [PHTHALIC ANHYDRIDE]		12	Short Term Exposure Limit (STEL):		EH40 WEL
Phthalic anhydride 85-44-9 [PHTHALIC ANHYDRIDE]		4	Time Weighted Average (TWA):		EH40 WEL
Hydroquinone 123-31-9 [HYDROQUINONE]		0,5	Time Weighted Average (TWA):		EH40 WEL

**Predicted No-Effect Concentration (PNEC):**

Name on list	Environmental Compartment	Exposure period	Value				Remarks
			mg/l	ppm	mg/kg	others	
Hydroquinone 123-31-9	aqua (freshwater)					0,114 µg/L	
Hydroquinone 123-31-9	aqua (marine water)					0,0114 µg/L	
Hydroquinone 123-31-9	sediment (freshwater)					0,98 µg/kg	
Hydroquinone 123-31-9	sediment (marine water)					0,097 µg/kg	
Hydroquinone 123-31-9	aqua (intermittent releases)					0,00134 mg/L	
Hydroquinone 123-31-9	soil					0,129 µg/kg	
Hydroquinone 123-31-9	STP					0,71 mg/L	
Phthalic anhydride 85-44-9	soil					0,173 mg/kg	
Phthalic anhydride 85-44-9	STP					10 mg/L	
Phthalic anhydride 85-44-9	sediment (freshwater)					3,8 mg/kg	
Phthalic anhydride 85-44-9	sediment (marine water)					0,38 mg/kg	
Phthalic anhydride 85-44-9	aqua (marine water)					0,1 mg/L	
Phthalic anhydride 85-44-9	aqua (intermittent releases)					5,6 mg/L	
Phthalic anhydride 85-44-9	aqua (freshwater)					1 mg/L	

**Derived No-Effect Level (DNEL):**

Name on list	Application Area	Route of Exposure	Health Effect	Exposure Time	Value	Remarks
Ethyl 2-cyanoacrylate 7085-85-0	Workers	Inhalation	Long term exposure - local effects		9,25 mg/m <sup>3</sup>	
Ethyl 2-cyanoacrylate 7085-85-0	Workers	Inhalation	Long term exposure - systemic effects		9,25 mg/m <sup>3</sup>	
Ethyl 2-cyanoacrylate 7085-85-0	general population	Inhalation	Long term exposure - local effects		9,25 mg/m <sup>3</sup>	
Ethyl 2-cyanoacrylate 7085-85-0	general population	Inhalation	Long term exposure - systemic effects		9,25 mg/m <sup>3</sup>	
Hydroquinone 123-31-9	Workers	Dermal	Long term exposure - systemic effects		128 mg/kg bw/day	
Hydroquinone 123-31-9	Workers	Inhalation	Long term exposure - systemic effects		7 mg/m <sup>3</sup>	
Hydroquinone 123-31-9	Workers	Inhalation	Long term exposure - local effects		1 mg/m <sup>3</sup>	
Hydroquinone 123-31-9	general population	Dermal	Long term exposure - systemic effects		64 mg/kg bw/day	
Hydroquinone 123-31-9	general population	Inhalation	Long term exposure - systemic effects		1,74 mg/m <sup>3</sup>	
Hydroquinone 123-31-9	general population	Inhalation	Long term exposure - local effects		0,5 mg/m <sup>3</sup>	
Phthalic anhydride 85-44-9	Workers	inhalation	Long term exposure - systemic effects		32,2 mg/m <sup>3</sup>	
Phthalic anhydride 85-44-9	Workers	Dermal	Long term exposure - systemic effects		10 mg/kg bw/day	
Phthalic anhydride 85-44-9	general population	inhalation	Long term exposure - systemic effects		8,6 mg/m <sup>3</sup>	
Phthalic anhydride 85-44-9	general population	Dermal	Long term exposure - systemic effects		5 mg/kg bw/day	
Phthalic anhydride 85-44-9	general population	oral	Long term exposure - systemic effects		5 mg/kg bw/day	

**Biological Exposure Indices:**

None

**8.2. Exposure controls:**

Respiratory protection:

Ensure adequate ventilation.

An approved mask or respirator fitted with an organic vapour cartridge should be worn if the product is used in a poorly ventilated area

Filter type: A

**Hand protection:**

Chemical-resistant protective gloves (EN 374).

Suitable materials for short-term contact or splashes (recommended: at least protection index 2, corresponding to > 30 minutes permeation time as per EN 374):

nitrile rubber (NBR;  $\geq 0.4$  mm thickness)

Suitable materials for longer, direct contact (recommended: protection index 6, corresponding to > 480 minutes permeation time as per EN 374):

nitrile rubber (NBR;  $\geq 0.4$  mm thickness)

This information is based on literature references and on information provided by glove manufacturers, or is derived by analogy with similar substances. Please note that in practice the working life of chemical-resistant protective gloves may be considerably shorter than the permeation time determined in accordance with EN 374 as a result of the many influencing factors (e.g. temperature). If signs of wear and tear are noticed then the gloves should be replaced.

Polyethylene or polypropylene gloves are recommended when using large volumes.

Do not use PVC, rubber or nylon gloves.

Please note that in practice the working life of chemical resistant gloves may be considerably reduced as a result of many influencing factors (e.g. temperature). Suitable risk assessment should be carried out by the end user. If signs of wear and tear are noticed then the gloves should be replaced.

**Eye protection:**

Wear protective glasses.

**Skin protection:**

Wear suitable protective clothing.

**SECTION 9: Physical and chemical properties****9.1. Information on basic physical and chemical properties**

Appearance	liquid black
Odor	Irritating
Odour threshold	No data available / Not applicable
pH	No data available / Not applicable
Initial boiling point	> 149 °C (> 300.2 °F)
Flash point	80 - 93 °C (176 - 199.4 °F); Tagliabue closed cup
Decomposition temperature	No data available / Not applicable
Vapour pressure (25 °C (77 °F))	0,6 mbar
Vapour pressure (50 °C (122 °F))	< 700 mbar
Density (20 °C (68 °F))	1,1 g/cm <sup>3</sup>
Bulk density	No data available / Not applicable
Viscosity	No data available / Not applicable
Viscosity (kinematic)	No data available / Not applicable
Explosive properties	No data available / Not applicable
Solubility (qualitative) (Solvent: Water)	Polymerises in presence of water.
Solubility (qualitative) (Solvent: Acetone)	Miscible
Solidification temperature	No data available / Not applicable
Melting point	No data available / Not applicable
Flammability	No data available / Not applicable
Auto-ignition temperature	No data available / Not applicable
Explosive limits	No data available / Not applicable
Partition coefficient: n-octanol/water	No data available / Not applicable
Evaporation rate	No data available / Not applicable
Vapor density	No data available / Not applicable
Oxidising properties	No data available / Not applicable

**9.2. Other information**

No data available / Not applicable



**SECTION 10: Stability and reactivity****10.1. Reactivity**

Rapid exothermic polymerization will occur in the presence of water, amines, alkalis and alcohols.

**10.2. Chemical stability**

Stable under recommended storage conditions.

**10.3. Possibility of hazardous reactions**

See section reactivity

**10.4. Conditions to avoid**

Stable under normal conditions of storage and use.

**10.5. Incompatible materials**

See section reactivity

**10.6. Hazardous decomposition products**

None if used for intended purpose.

**SECTION 11: Toxicological information****11.1. Information on toxicological effects****General toxicological information:**

The mixture is classified based on the available hazard information for the ingredients as defined in the classification criteria for mixtures for each hazard class or differentiation in Annex I to Regulation 1272/2008/EC. Relevant available health/ecological information for the substances listed under Section 3 is provided in the following.

**STOT-single exposure:**

May cause respiratory irritation.

**Oral toxicity:**

Cyanoacrylates are considered to have relatively low toxicity. Acute oral LD50 is >5000mg/kg (rat). It is almost impossible to swallow as it rapidly polymerises in the mouth.

**Inhalative toxicity:**

Prolonged exposure to high concentrations of vapours may lead to chronic effects in sensitive individuals  
In dry atmosphere with < 50% humidity, vapours may irritate the eyes and respiratory system

**Skin irritation:**

Causes skin irritation.

Bonds skin in seconds. Considered to be of low toxicity: acute dermal LD50 (rabbit)>2000mg/kg

Due to polymerisation at the skin surface allergic reaction is unlikely to occur

**Eye irritation:**

Causes serious eye irritation.

Liquid product will bond eyelids. In a dry atmosphere (RH<50%) vapours may cause irritation and lachrymatory effect

**Sensitizing:**

May cause allergic reaction.

**Acute oral toxicity:**

Hazardous components CAS-No.	Value type	Value	Route of application	Exposure time	Species	Method
Ethyl 2-cyanoacrylate 7085-85-0	LD50	> 5.000 mg/kg	oral		rat	OECD Guideline 401 (Acute Oral Toxicity)
Hydroquinone 123-31-9	LD50	367 mg/kg	oral		rat	OECD Guideline 401 (Acute Oral Toxicity)
Phthalic anhydride 85-44-9	LD50	1.530 mg/kg	oral		rat	

**Acute dermal toxicity:**

Hazardous components CAS-No.	Value type	Value	Route of application	Exposure time	Species	Method
Ethyl 2-cyanoacrylate 7085-85-0	LD50	> 2.000 mg/kg	dermal		rabbit	OECD Guideline 402 (Acute Dermal Toxicity)
Phthalic anhydride 85-44-9	LD50	> 10.000 mg/kg	dermal		rabbit	

**Skin corrosion/irritation:**

Hazardous components CAS-No.	Result	Exposure time	Species	Method
Ethyl 2-cyanoacrylate 7085-85-0	slightly irritating	24 h	rabbit	OECD Guideline 404 (Acute Dermal Irritation / Corrosion)

**Serious eye damage/irritation:**

Hazardous components CAS-No.	Result	Exposure time	Species	Method
Ethyl 2-cyanoacrylate 7085-85-0	irritating	72 h	rabbit	OECD Guideline 405 (Acute Eye Irritation / Corrosion)
Phthalic anhydride 85-44-9	highly irritating		rabbit	

**Respiratory or skin sensitization:**

Hazardous components CAS-No.	Result	Test type	Species	Method
Ethyl 2-cyanoacrylate 7085-85-0	not sensitising		guinea pig	
Hydroquinone 123-31-9	sensitising	Guinea pig maximisation test	guinea pig	
Phthalic anhydride 85-44-9	sensitising	in vivo	guinea pig	
Phthalic anhydride 85-44-9	sensitising	Mouse local lymphnode assay (LLNA)	mouse	Mouse local lymphnode assay (LLNA)

**Germ cell mutagenicity:**

Hazardous components CAS-No.	Result	Type of study / Route of administration	Metabolic activation / Exposure time	Species	Method
Ethyl 2-cyanoacrylate 7085-85-0	negative	bacterial reverse mutation assay (e.g Ames test)			OECD Guideline 471 (Bacterial Reverse Mutation Assay)
	negative	mammalian cell gene mutation assay	with and without		OECD Guideline 476 (In vitro Mammalian Cell Gene Mutation Test)
	negative	in vitro mammalian chromosome aberration test	with and without		OECD Guideline 473 (In vitro Mammalian Chromosome Aberration Test)
Hydroquinone 123-31-9	negative	bacterial reverse mutation assay (e.g Ames test)	with and without		EU Method B.13/14 (Mutagenicity)
Phthalic anhydride 85-44-9	negative	bacterial reverse mutation assay (e.g Ames test)	with and without		

**Repeated dose toxicity**

Hazardous components CAS-No.	Result	Route of application	Exposure time / Frequency of treatment	Species	Method
Hydroquinone 123-31-9	LOAEL= $\leq$ 500 mg/kg	oral: gavage	14 days 5 days/week. 12 doses	rat	OECD Guideline 407 (Repeated Dose 28-Day Oral Toxicity in Rodents)
Hydroquinone 123-31-9	NOAEL= $\geq$ 250 mg/kg	oral: gavage	14 days 5 days/week. 12 doses	rat	OECD Guideline 407 (Repeated Dose 28-Day Oral Toxicity in Rodents)

**SECTION 12: Ecological information****General ecological information:**

Biological and Chemical Oxygen Demands (BOD and COD) are insignificant.

The mixture is classified based on the available hazard information for the ingredients as defined in the classification criteria for mixtures for each hazard class or differentiation in Annex I to Regulation 1272/2008/EC. Relevant available health/ecological information for the substances listed under Section 3 is provided in the following.

**12.1. Toxicity****Ecotoxicity:**

Do not empty into drains / surface water / ground water.

Hazardous components CAS-No.	Value type	Value	Acute Toxicity Study	Exposure time	Species	Method
Hydroquinone 123-31-9	LC50	0,638 mg/l	Fish	96 h	Oncorhynchus mykiss	OECD Guideline 203 (Fish, Acute Toxicity Test)
Hydroquinone 123-31-9	EC50	0,134 mg/l	Daphnia	48 h	Daphnia magna	OECD Guideline 202 (Daphnia sp. Acute Immobilisation Test)
Hydroquinone 123-31-9	EC50	0,335 mg/l	Algae	72 h	Selenastrum capricornutum (new name: Pseudokirchnerella subcapitata)	OECD Guideline 201 (Alga, Growth Inhibition Test)
Hydroquinone 123-31-9	NOEC	0,0057 mg/l	chronic Daphnia	21 d	Daphnia magna	OECD 211 (Daphnia magna, Reproduction Test)
Phthalic anhydride 85-44-9	LC50	313 mg/l	Fish	48 h	Leuciscus idus	DIN 38412-15
Phthalic anhydride 85-44-9	EC50	68 mg/l	Algae	72 h	Selenastrum sp.	OECD Guideline 201 (Alga, Growth Inhibition Test)

**12.2. Persistence and degradability****Persistence and Biodegradability:**

No data available.

Hazardous components CAS-No.	Result	Route of application	Degradability	Method
---------------------------------	--------	-------------------------	---------------	--------

Ethyl 2-cyanoacrylate 7085-85-0		aerobic	57 %	OECD Guideline 301 D (Ready Biodegradability: Closed Bottle Test)
Hydroquinone 123-31-9	readily biodegradable	aerobic	75 - 81 %	EU Method C.4-E (Determination of the "Ready" Biodegradability Closed Bottle Test)
Phthalic anhydride 85-44-9		aerobic	90 %	OECD Guideline 301 D (Ready Biodegradability: Closed Bottle Test)

**12.3. Bioaccumulative potential / 12.4. Mobility in soil****Mobility:**

Cured adhesives are immobile.

**Bioaccumulative potential:**

No data available.

Hazardous components CAS-No.	LogKow	Bioconcentration factor (BCF)	Exposure time	Species	Temperature	Method
Ethyl 2-cyanoacrylate 7085-85-0	0,776				22 °C	EU Method A.8 (Partition Coefficient)
Hydroquinone 123-31-9	0,59					EU Method A.8 (Partition Coefficient)
Phthalic anhydride 85-44-9	1,6					

**12.5. Results of PBT and vPvB assessment**

Hazardous components CAS-No.	PBT/vPvB
Hydroquinone 123-31-9	Not fulfilling PBT (persistent/bioaccumulative/toxic) criteria
Phthalic anhydride 85-44-9	Not fulfilling Persistent, Bioaccumulative and Toxic (PBT), very Persistent and very Bioaccumulative (vPvB) criteria.

**12.6. Other adverse effects**

No data available.

**SECTION 13: Disposal considerations****13.1. Waste treatment methods**

Product disposal:

Cured adhesive: Dispose of as water insoluble non-toxic solid chemical in authorised landfill or incinerate under controlled conditions.

Dispose of in accordance with local and national regulations.

Contribution of this product to waste is very insignificant in comparison to article in which it is used

Disposal of uncleaned packages:

After use, tubes, cartons and bottles containing residual product should be disposed of as chemically contaminated waste in an authorised legal land fill site or incinerated.

Disposal must be made according to official regulations.

Waste code

08 04 09 waste adhesives and sealants containing organic solvents and other dangerous substances

The valid EWC waste code numbers are source-related. The manufacturer is therefore unable to specify EWC waste codes for the articles or products used in the various sectors. The EWC codes listed are intended as a recommendation for users. We will be happy to advise you.

**SECTION 14: Transport information****14.1. UN number**

ADR	Not dangerous goods
RID	Not dangerous goods
ADN	Not dangerous goods
IMDG	Not dangerous goods
IATA	3334

**14.2. UN proper shipping name**

ADR	Not dangerous goods
RID	Not dangerous goods
ADN	Not dangerous goods
IMDG	Not dangerous goods
IATA	Aviation regulated liquid, n.o.s. (Cyanoacrylate ester)

**14.3. Transport hazard class(es)**

ADR	Not dangerous goods
RID	Not dangerous goods
ADN	Not dangerous goods
IMDG	Not dangerous goods
IATA	9

**14.4. Packaging group**

ADR	Not dangerous goods
RID	Not dangerous goods
ADN	Not dangerous goods
IMDG	Not dangerous goods
IATA	III

**14.5. Environmental hazards**

ADR	not applicable
RID	not applicable
ADN	not applicable
IMDG	not applicable
IATA	not applicable

**14.6. Special precautions for user**

ADR	not applicable
RID	not applicable
ADN	not applicable
IMDG	not applicable
IATA	Primary packs containing less than 500ml are unregulated by this mode of transport and may be shipped unrestricted.

**14.7. Transport in bulk according to Annex II of MARPOL 73/78 and the IBC Code**

not applicable

**SECTION 15: Regulatory information****15.1. Safety, health and environmental regulations/legislation specific for the substance or mixture**

VOC content < 3,00 %  
(2010/75/EC)

**15.2. Chemical safety assessment**

A chemical safety assessment has been carried out.

## SECTION 16: Other information

The labelling of the product is indicated in Section 2. The full text of all abbreviations indicated by codes in this safety data sheet are as follows:

- H302 Harmful if swallowed.
- H315 Causes skin irritation.
- H317 May cause an allergic skin reaction.
- H318 Causes serious eye damage.
- H319 Causes serious eye irritation.
- H334 May cause allergy or asthma symptoms or breathing difficulties if inhaled.
- H335 May cause respiratory irritation.
- H341 Suspected of causing genetic defects.
- H351 Suspected of causing cancer.
- H400 Very toxic to aquatic life.
- H410 Very toxic to aquatic life with long lasting effects.

### Further information:

This information is based on our current level of knowledge and relates to the product in the state in which it is delivered. It is intended to describe our products from the point of view of safety requirements and is not intended to guarantee any particular properties.

### Label elements (DPD):

Xi - Irritant



### Risk phrases:

R36/37/38 Irritating to eyes, respiratory system and skin.

### Safety phrases:

- S23 Do not breathe vapour.
- S24/25 Avoid contact with skin and eyes.
- S26 In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

### Additional labeling:

Cyanoacrylate. Danger. Bonds skin and eyes in seconds. Keep out of the reach of children.

Contains Phthalic anhydride, Hydroquinone. May produce an allergic reaction.

**Relevant changes in this safety data sheet are indicated by vertical lines at the left margin in the body of this document. Corresponding text is displayed in a different color on shadowed fields.**

## Annex - Exposure Scenarios:

Exposure Scenarios for ethyl 2-cyanoacrylate can be downloaded under the following link:  
[http://mymds.henkel.com/mymds/.470833.en.ANNEX\\_DE.15743123.0.DE.pdf](http://mymds.henkel.com/mymds/.470833.en.ANNEX_DE.15743123.0.DE.pdf)  
Alternatively they can be accessed on the internet site [www.mymds.henkel.com](http://www.mymds.henkel.com) by entering number 470833.

# LOCTITE<sup>®</sup> 480<sup>™</sup>

September 2015

## PRODUCT DESCRIPTION

LOCTITE<sup>®</sup> 480<sup>™</sup> provides the following product characteristics:

<b>Technology</b>	Cyanoacrylate
<b>Chemical Type</b>	Ethyl cyanoacrylate
<b>Appearance (uncured)</b>	Black liquid <sup>LMS</sup>
<b>Components</b>	One part - requires no mixing
<b>Viscosity</b>	Low
<b>Cure</b>	Humidity
<b>Application</b>	Bonding
<b>Key Substrates</b>	Metals, Plastics and Rubbers

LOCTITE<sup>®</sup> 480<sup>™</sup> is a rubber toughened adhesive with increased flexibility and peel strength along with enhanced resistance to shock.

## NSF International

**Certified to ANSI/NSF Standard 61** for use in commercial and residential potable water systems not exceeding 82° C. **Note:** This is a regional approval. Please contact your local Technical Service Center for more information and clarification.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.05
Flash Point - See SDS	
Viscosity, Cone & Plate, mPa·s (cP): Temperature: 25 °C, Shear Rate: 1,000 s <sup>-1</sup>	100 to 200 <sup>LMS</sup>
Viscosity, Brookfield - LVF, 25 °C, mPa·s (cP): Spindle 1, speed 6 rpm	100 to 200

## TYPICAL CURING PERFORMANCE

Under normal conditions, the atmospheric moisture initiates the curing process. Although full functional strength is developed in a relatively short time, curing continues for at least 24 hours before full chemical/solvent resistance is developed.

## Cure Speed vs. Substrate

The rate of cure will depend on the substrate used. The table below shows the fixture time achieved on different materials at 22 °C / 50 % relative humidity. This is defined as the time to develop a shear strength of 0.1 N/mm<sup>2</sup>.

Fixture Time, seconds:

Steel (degreased)	60 to 120
Aluminum	10 to 30
Zinc dichromate	50 to 150
Neoprene	<20
Rubber, nitrile	<20
ABS	20 to 50
PVC	50 to 100
Polycarbonate	30 to 90
Phenolic	20 to 60

## Cure Speed vs. Bond Gap


The rate of cure will depend on the bondline gap. Thin bond lines result in high cure speeds, increasing the bond gap will decrease the rate of cure.

## Cure Speed vs. Activator

Where cure speed is unacceptably long due to large gaps, applying activator to the surface will improve cure speed. However, this can reduce ultimate strength of the bond and therefore testing is recommended to confirm effect.

## Cure Speed vs. Humidity

The rate of cure will depend on the ambient relative humidity. The following graph shows the tensile strength developed with time on Buna N rubber at different levels of humidity.



**TYPICAL PROPERTIES OF CURED MATERIAL**

Cured for 24 hours @ 22 °C

**Physical Properties:**

Coefficient of Thermal Expansion, ISO 11359-2, K<sup>-1</sup> 80×10<sup>-6</sup>  
 Coefficient of Thermal Conductivity ISO 8302, 0.1 W/(m·K)  
 Glass Transition Temperature, ISO 11359-2, 150 °C

**Electrical Properties:**

Volume Resistivity, IEC 60093, Ω·cm 10×10<sup>15</sup>  
 Surface Resistivity, IEC 60093, Ω 10×10<sup>15</sup>  
 Dielectric Breakdown Strength, IEC 60243-1, kV/mm 25  
 Dielectric Constant / Dissipation Factor, IEC 60250:  
 0.1 kHz 2.65 / <0.02  
 1 kHz 2.75 / <0.02  
 10 kHz 2.75 / <0.02

**TYPICAL PERFORMANCE OF CURED MATERIAL**

**Adhesive Properties**

Cured for 30 seconds @ 22 °C

Tensile Strength, ISO 6922:

Buna-N N/mm<sup>2</sup> ≥1.8<sup>LMS</sup>  
 (psi) (≥260)

Cured for 24 hours @ 22 °C

Lap Shear Strength, ISO 4587:

Steel (grit blasted) N/mm<sup>2</sup> 22 to 30  
 (psi) (3,200 to 4,400)  
 Aluminum (etched) N/mm<sup>2</sup> 14 to 22  
 (psi) (2,000 to 3,200)  
 Zinc dichromate N/mm<sup>2</sup> 8 to 15  
 (psi) (1,200 to 2,200)  
 ABS N/mm<sup>2</sup> 6 to 20  
 (psi) (870 to 2,900)  
 PVC N/mm<sup>2</sup> 4 to 20  
 (psi) (580 to 2,900)  
 Phenolic N/mm<sup>2</sup> 5 to 15  
 (psi) (730 to 2,200)  
 Polycarbonate N/mm<sup>2</sup> 5 to 20  
 (psi) (730 to 2,900)  
 Nitrile N/mm<sup>2</sup> 5 to 15  
 (psi) (730 to 2,200)  
 Neoprene N/mm<sup>2</sup> 5 to 15  
 (psi) (730 to 2,200)

Tensile Strength, ISO 6922:

Steel (grit blasted) N/mm<sup>2</sup> 12 to 25  
 (psi) (1,700 to 3,600)  
 Buna-N N/mm<sup>2</sup> 5 to 15  
 (psi) (730 to 2,200)

Cured for 24 hours @ 22 °C, followed by 48 hours @ 120 °C, tested @ 22 °C

Lap Shear Strength, ISO 4587:

Steel (grit blasted) N/mm<sup>2</sup> ≥18.0<sup>LMS</sup>  
 (psi) (≥2,610)


**TYPICAL ENVIRONMENTAL RESISTANCE**

Cured for 1 week @ 22 °C

Lap Shear Strength, ISO 4587:  
 Steel (grit blasted)


**Hot Strength**

Tested at temperature



**Heat Aging**

Aged at temperature indicated and tested @ 22 °C



**Chemical/Solvent Resistance**

Aged under conditions indicated and tested @ 22 °C.

Environment	°C	% of initial strength		
		100 h	500 h	1000 h
Motor oil	40	85	85	85
Gasoline	22	90	70	70
Ethanol	22	95	95	80
Isopropanol	22	75	75	75
Freon TA	22	90	90	85
Heat/humidity 95% RH	40	80	80	65

Lap Shear Strength, ISO 4587:

Polycarbonate

Environment	°C	% of initial strength		
		100 h	500 h	1000 h
Heat/humidity 95% RH	40	100	100	100



**GENERAL INFORMATION**

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.**

**For safe handling information on this product, consult the Safety Data Sheet (SDS).**

**Directions for use:**

1. For best performance bond surfaces should be clean and free from grease.
2. This product performs best in thin bond gaps (0.05 mm).
3. Excess adhesive can be dissolved with Loctite cleanup solvents, nitromethane or acetone.

**Loctite Material Specification<sup>LMS</sup>**

LMS dated December 5, 2003. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

**Storage**

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 2 °C to 8 °C. Storage below 2 °C or greater than 8 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\mu\text{m} / 25.4 = \text{mil}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic**

**Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

## Reference 1.6